



# W. DRESSELHAUS ENGINEERING

Co. Reg. No. 86/082

P.O. Box 1483  
Telephone 09-264-64-204745/206459  
Fax 09-264-64-204751  
E-Mail: [dresse@afrika.com.na](mailto:dresse@afrika.com.na)  
NR 23 Circumferential Road  
WALVIS BAY  
NAMIBIA

## Roughness Test on Cylinder Liners Bergen Diesel C-Type Order No 116704

Average surface roughness to be in range:

Rz	8 - 14 $\mu\text{m}$
Ra	0.8 - 1.4 $\mu\text{m}$

### Result

Ra	1.177 $\mu\text{m}$
Rq	1.795 $\mu\text{m}$

Rz	11.841 $\mu\text{m}$
Rt	14.68 $\mu\text{m}$

Rp	2.319 $\mu\text{m}$
Rv	9.495 $\mu\text{m}$

RS	0.1016 $\mu\text{m}$
RSm	0.1436 $\text{mm}$

RSk	-2.558
-----	--------

